Codice: 5W70-BZ70

Prop shark



Highly slippery biocide-free antifouling paint

Highly slippery biocide-free antifouling paint, with excellent expansion, scratch-resistant, hard and elastic. It is characterized by high slipperiness and anti-adhesion, which facilitates surface cleaning, used as a finishing coat in the nautical sector, reduces the attack of marine fouling especially both hard and soft fouling Recommended for propellers where speed is the turbulence generated by the rotation helps to keep the surface clean. Biocide-free product.

Techical Characteristics		
Shelf life min+10°C max+35°C	18 months in unopened cans	ı
Paint Type	Two components	
Binder type A	Poliacrylic	
Binder type B	Aliphatic Isocyanate	
Code & colour A	5W7062 Transparent	
Code & colour B	8Z7063 Transparent	
Specific gravity kg/lt (±0,05)	1.020 (A) / 0.990 (B)	
Solids content (volume) ±2	40%	
Viscosity Ford ø 8 at 20°C ±2	20 +/- 5 s	
Shelf life +23°C (±2)	18 months in unopened cans	

Application Data		
Application: by spreading	Ready to use	
Application: Spray	Ready to use-max 10%	
	Thinner 203	
Application	Dilution	
Mixing ratio A+B by volume	100pp Sol. A + 50pp Sol. B	
Mixing ratio A+B by weight	100pp Sol. A + 50pp Sol. B	
Pot life A+B (20°C)	use within 2-3 hours	
Brush-Roller	pronta al uso	
Spray	10% max se serve	
Dust dry	30 minutes (20c)	
Recoat time	no later than 1 hour for the	
	second coat - after sanding	
Application temperature	Between +10 C and +40 C	
Dry film thickness advised	40 microns per hand	
Theoret. coverage m2/Lt	11-13 (= m2 / Kg)	

PREPARATION OF THE SUPPORT AND APPLICATION CYCLE

Supports:

Aluminium, light alloys and other types of surfaces. The support must necessarily be pre-treated, abraded - roughened. Then apply 1 coat of PROPSHARK at the appropriate thickness. A second coat is possible within 1 hour of the first coat. after 2 hours apply after roughening, otherwise adhesion could be compromised.









Codice: 5W70-BZ70 **Prop shark**

SAFETY PRECAUTIONS

Before starting paint application please carefully read all the safety precautions indicated on the label of each can or in the product safety data sheet available on request. For further information please do not hesitate to contact our technical staff.

NOTES

The above information is given to the best of our current knowledge, however, because the conditions of use of our products are beyond our control, no warranty is given or to be implied in respect of such information. Our technical staff can be contacted to study customer's specific requirements involving our products in order to enable their most effective use. Dilution rates and drying times must be considered only indicative, mainly related to a temperature of 20 °C (68°F) and may vary according to prevailing temperature, in presence of particular weather conditions or depending on application procedures.





